

IN THE CLAIMS

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (currently amended) An amorphous iron-based alloy having a composition consisting essentially of about 70-87 atom percent iron, up to about 20 atom percent of the iron being optionally replaced by cobalt and up to about 3 atom percent of the iron being optionally replaced by nickel, manganese, vanadium, titanium or molybdenum, the balance of elements present comprising a member selected from the group consisting of boron, silicon and carbon, said alloy being heat-treated to induce a linear BH characteristic within an applied field ranging from about -15 Oe to + 15 Oe and low magnetic loss.
2. (original) A heat-treated amorphous iron-based alloy as recited by claim 1, having a saturation magnetic induction exceeding about 10 kG ,or 1 Tesla;
3. (original) An amorphous iron-based alloy as recited by claim 1, said alloy having the form of a strip having a predetermined easy magnetization direction and having been heat-treated in a magnetic field, the magnitude of said magnetic field ranging from about 50 Oe (4,000 A/m) to about 2,000 Oe (160,000 A/m), and said field having been applied perpendicular to the predetermined easy magnetization direction of said strip.
4. (original) An amorphous iron-based alloy as recited by claim 1, said alloy having been heat-treated at a temperature near the Curie temperature of the alloy.

5. (original) An amorphous iron-based alloy as recited by claim 4, said alloy having been heat-treated at a temperature high enough to allow atomic diffusion or rearrangement of its constituents.
6. (currently amended) An amorphous iron-based alloy having a composition consisting essentially of about 70-87 atom percent iron, up to about 20 atom percent of the iron being optionally replaced by cobalt and up to about 3 atom percent of the iron being optionally replaced by nickel, manganese, vanadium, titanium or molybdenum, the balance of elements present comprising a member selected from the group consisting of boron, silicon and carbon, said alloy being heat-treated in the presence of a magnetic field to induce a linear BH characteristic within an applied field ranging from about -15 Oe to + 15 Oe and low magnetic loss.
7. (original) A heat-treated amorphous iron-based alloy as recited by claim 6, having a saturation magnetic induction exceeding about 10 kG, or 1 Tesla;
8. (original) An amorphous iron-based alloy as recited by claim 6, said alloy having the form of a strip having a predetermined easy magnetization direction and said magnetic field having a magnitude ranging from about 50 Oe (4,000 A/m) to about 2,000 Oe (160,000 A/m), and having been applied perpendicular to the predetermined easy magnetization direction of said strip.
9. (original) An amorphous iron-based alloy as recited by claim 6, said alloy having been heat-treated at a temperature near the Curie temperature of the alloy.

10. (original) An amorphous iron-based alloy as recited by claim 9, said alloy having been heat-treated at a temperature high enough to allow atomic diffusion or rearrangement of its constituents.